



Monarplan FMX

World Reference
in Waterproofing

Technical Product Data



Surface Topside	Dull colour 652
Surface Bottomside	Dull colour 655
Material	PVC-P
Type of Reinforcement	Non-wick Polyester Reinforcement

Product specifications	Methode	Unit	Requirement	Tolerance
Mass per m2	EN 1849-2	gr/m2	1575-1950-2340-2550	-5/+10%
Length	EN 1848-2	m	15 - 20	-0/+5%
Width	EN 1848-2	m	0.75-1.06-1.50-2.12	-0,5/+1%
Thickness	EN 1849-2	mm	1.2 - 1.5 - 1.8 - 2.0	-5/+10%
External fire performance	EN 13501-5	-	Broof t1-t2-t3	-
	DIN 4102	-	B1	-
Reaction to fire	EN 13501-1	-	Class E	-
Watertightness	EN 1928(B)	kPa	≥ 400	-
Water vapour diffusion value	EN 1931	μ	10.000	+/- 30%
Tensile strength	EN 12311 method A	N/50mm	≥ 900	-
Elongation at break	EN 12311 method A	%	≥ 15	-
Tear strength	EN 12310-2	N	≥ 200	-
Dimensional stability	EN 1107-1	%	≤ 0,5	-
Root resistance	EN 13948	-	n.a	-
Resistance to static loading	EN 12730	kg	≥ 20	-
Resistance to dynamic loading	EN 12691	mm	10	-
Nail tear strength	EN 12310-1	N	≥ 300	-
Peel strength overlap	EN 12316-2	N/50mm	≥ 100	-
Tensile strength overlap	EN 12317-2	N/50mm	≥ 700	-
Low temperature folding	EN 495-5	°C	≤ - 30	-

Article Number

xxxxxx

Description

Monarplan FMX is a single-ply, mechanically fastened Roofingsystem.

Monarplan FMX is non bitumen compatible, extra durable.

Certification

CTG-613, EN-13956 0958-CPD-DK034

Application

According to application guidelines Icopal Synthetic Membranes BV.

Delivery

Delivery

Monarplan FMX Rolls are delivered on pallets, covered with PE Foil.

Storage and transportation.

Monarplan FMX must be stored horizontal on a flat and dry surface, at a temperature between 0 en 40°C. During storage direct sunlight has to be avoided.

Productidentification:

Information on the roll:

- Monarplan FMX
- Articlenuumber, rolllength, width, thickness, certificationnumber.